



d	M3	M4	M5	M6	M8	M10	M12
s	5.5	7	8	10	13	17	19
e	6.01	7.66	8.79	11.05	14.38	18.9	21.1
m	1.8	2.2	2.7	3.2	4	5	6

d	M14	M16	M18	M20	M22	M24	M27
s	22	24	27	30	32	36	41
e	24.49	26.75	29.56	32.95	35.03	39.55	45.2
m	7	8	9	10	11	12	13.5

d	M30	M33	M36	M39	M42
s	46	50	55	60	65
e	50.85	55.37	60.79	66.44	71.3
m	15	16.5	18	19.5	21

COMPOSICIÓN QUÍMICA (en %)

	C	Mn	Si	P	S	Cr	Ni	Cu
Mínimo	--	--	--	--	--	15,00	8,000	--
Máximo	0,100	2,000	1,000	0,050	0,030	20,00	19,00	4,000

CARACTERÍSTICAS MECÁNICAS

	Mínimo	Máximo
Resistencia Tracción – N/mm2	700,00000	--
Limite Elasticidad – N/mm2	450,00000	--