



d	M3	M4	M5	M6	M8	M10
t min.	1.2	1.6	2	2.4	3.2	4
n	0.8	1	1.2	1.6	2	2.5
k	1.65	2.2	2.5	3	4	5
dk	5.6	7.5	9.2	11	14.5	18
f	0.75	1	1.2	1.5	2	2.5
L	de 5 a 50	de 5 a 70	de 6 a 100	de 8 a 100	de 10 a 100	de 16 a 100

COMPOSICIÓN QUÍMICA (en %)

	C	Mn	Si	P	S	Cr	Ni	Cu
Mínimo	--	--	--	--	--	15,00	8,000	--
Máximo	0,100	2,000	1,000	0,050	0,030	20,00	19,00	4,000

CARACTERÍSTICAS MECÁNICAS

	Mínimo	Máximo
Resistencia Tracción – N/mm ²	700,00000	--
Limite Elasticidad – N/mm ²	450,00000	--