

EN 1.4305 / AISI 303

Euronorm	Nom.	AISI / ASTM / UNS	
1.4305	X8CrNiS18-9	303	

Composición Química

Tipo	C	Si	Mn	P	S	Cr	Ni	Mo	Ti	Cu	Otros
ACX 73	<=0.10	<=0.75	1.50-2.00	<=0.040	0.20-0.30	17.00-19.00	9.00-10.00	-	-	-	N(ppm) <1100
ACX 76	<=0.10	<=0.75	1.50-2.00	<=0.040	0.28-0.35	17.00-19.00	8.00-9.00	-	-	-	N(ppm) <1100